

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 25/00, 15/28	A1	(11) International Publication Number: WO 96/13284 (43) International Publication Date: 9 May 1996 (09.05.96)
<p>(21) International Application Number: PCT/GB95/02542</p> <p>(22) International Filing Date: 30 October 1995 (30.10.95)</p> <p>(30) Priority Data: 9421969.8 28 October 1994 (28.10.94) GB</p> <p>(71) Applicant (for all designated States except US): INNOVATIVE TECHNOLOGIES LIMITED [GB/GB]; Winsford Industrial Estate, Road Three, Winsford, Cheshire CW7 3PD (GB).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): QIN, Yimin [GB/GB]; 123 Victoria Road, Northwich, Cheshire CW9 5RQ (GB). GILDING, Keith, Dennis [GB/GB]; Nepenthe, Winsford Road, Wettenhall, Winsford, Cheshire CW7 4DL (GB).</p> <p>(74) Agent: ATKINSON, Peter, Birch; Marks & Clerk, Sussex House, 83-85 Mosley Street, Manchester M2 3LG (GB).</p>		<p>(81) Designated States: AL, AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, LS, MW, SD, SZ, UG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: WOUND TREATMENT COMPOSITION</p> <p>(57) Abstract</p> <p>A composition for use in treating a wound, e.g. cavity wounds, comprises a hydrogel containing O-carboxymethyl chitosan or N,O-carboxymethyl chitosan and a plasticising compound.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

WOUND TREATMENT COMPOSITION

The present invention relates to compositions which are useful in the treatment of wounds. The invention relates more particularly to such compositions which incorporate O-carboxymethyl chitosan (OCC) or N-, O- carboxymethyl chitosan (NOCC) which are a water soluble derivatives of chitin.

NOCC is a known material and its preparation is disclosed for example in US-A-4,619,995. Briefly NOCC may be prepared by a solid phase reaction between chitosan and monochloroacetic acid under alkaline conditions. The degree of substitution can be varied but is typically 0.6 to 1.0. OCC may be produced by a similar procedure effected to give a degree of substitution of 0.3-0.5.

According to a first aspect of the present invention there is provided a composition for use in treating a wound comprising a hydrogel containing OCC or NOCC and a plasticising compound.

Compositions in accordance with the invention are useful in the treatment of cavity wounds, e.g. decubitus ulcers. The compositions are introduced into the wound and pressed firmly into the base thereof. For preference the wound is then covered and sealed by a film having a high MVTR, typically 3,000 to 12,000 g m⁻² 24hr⁻¹ (e.g. hydroderm (ex Wilshire Medical) or IT425 or IT625 (ex Innovative Technologies)). The compositions may also be used in the treatment of sinuses.

Preferred compositions in accordance with the invention have a viscosity in the range 20,000 to 100,000 cP.

Compositions in accordance with the invention will generally contain a maximum of 5% by weight of OCC and/or NOCC. Typically the OCC or NOCC content will be in the range 2-4%.

The plasticiser will generally be present in a maximum amount of 20% by weight, more usually in the range 2-20% by weight.

Examples of plasticiser include polyhydroxy compounds, e.g. glycerol, sorbitol, propylene glycol, and polyethylene glycol (a preferred example of which is PEG 400).

The most preferred plasticiser glycerol.

The aqueous phase of the gel will for preference comprise isotonic buffered saline, e.g. phosphate buffered saline.

Additional components may be included in the composition to enhance their healing properties. Examples include antimicrobial agents which may be used at a level of 1-2% of the composition. A preferred anti-microbial agent is chlorhexidine gluconate.

Antimicrobial properties may also be achieved by use of enzymes, e.g. glucose oxidase/lactic acid peroxidase enzymes as a natural disinfection system activated by glucose (present in exudate).

A further possibility is to include a component, e.g. pectin, which facilitates wound debridement. This component may for example be used in an amount up to 20%, more preferably up to 10%, e.g. 0.05-1% by weight.

Compositions for use in accordance with the invention may be produced in various ways. For example a composition may be produced by dissolving the required

amounts of OCC or NOCC (e.g. 3-5%), plasticiser and any other components in phosphate buffered saline at 90°C then cooling. The composition may be sterilised by autoclaving at 120°C for 15 minutes.

The gels obtained may be incorporated into a convenient delivery system, e.g. a syringe, sachet, tube or squeeze bottle, for introduction into a wound.

The invention is illustrated by the following non-limiting Example.

Example

A gel was produced by dissolving 3-4% NOCC and 1-2% high methoxy pectin (Bulmers) in isotonic phosphate buffered saline at pH 7 with 2% glycerol. The gel was filled into a vessel and autoclaved at 120°C for 15 minutes. The viscosity of the gel reduced slightly during autoclaving but by no more than 10%.

CLAIMS

1. A composition for use in treating a wound comprising a hydrogel containing OCC or NOCC and a plasticising compound.
2. A composition as claimed in claim 1 containing a maximum of 5% by weight of OCC and/or NOCC.
3. A composition as claimed in claim 2 containing 2-4% by weight OCC and/or NOCC.
4. A composition as claimed in any one of claims 1 to 3 wherein the plasticiser is present in an amount of less than 20% by weight.
5. A composition as claimed in any one of the preceding claims wherein the plasticiser is a polyhydroxy compound.
6. A composition as claimed in claim 5 wherein the plasticiser is glycerol, sorbitol, propylene glycol or polyethylene glycol.
7. A composition as claimed in any one of the preceding claims wherein the aqueous phase of the gel comprises isotonic buffered saline.

8. A composition as claimed in any one of the preceding claims additionally incorporating an anti-microbial agent.

9. A composition as claimed in claim 8 wherein the anti-microbial agent is chlorhexidine gluconate.

10. A composition as claimed in any one of claims 1 to 8 incorporating glucose oxidase/lactic acid hydrogenase enzymes.

11. A composition as claimed in any one of the preceding claims containing pectin for wound debridement.

12. A composition as claimed in any one of the preceding claims having a viscosity in the range 20,000 to 100,000 cP.

13. A composition as claimed in any one of the preceding claims which has been sterilised by autoclaving.

14. A composition as claimed in any one of the preceding claims incorporated in a delivery system.

15. The combination of a composition as claimed in any one of the preceding claims and a film having a high MVTR capability.
16. The combination as claimed in claim 15 wherein the film has an MVTR of 3,000 to 12,000 $\text{g m}^{-2} \text{24hr}^{-1}$.

INTERNATIONAL SEARCH REPORT

International Application No

PL./GB 95/02542

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>JOURNAL OF BIOACTIVE AND COMPATIBLE POLYMERS, vol. 5, no. 4, October 1990 US, pages 396-410, XP 000213548 R.A.A.MUZZARELLI ET AL. 'N-CARBOXYBUTYL CHITOSAN AND FIBRIN GLUE IN CUTANEOUS REPAIR PROCESSES' see abstract</p> <p>-----</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PL./GB 95/02542

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-3903268	02-09-75	US-A- 3632754	04-01-72
US-A-4659700	21-04-87	NONE	
EP-A-0426368	08-05-91	AT-T- 116555	15-01-95
		AU-B- 612085	27-06-91
		CA-A- 2028709	01-05-91
		DE-D- 69015775	16-02-95
		DE-T- 69015775	11-05-95
		ES-T- 2066152	01-03-95
		JP-A- 3167201	19-07-91
		JP-B- 7090041	04-10-95
		US-A- 5093319	03-03-92
EP-A-0356060	28-02-90	US-A- 4956350	11-09-90
		AU-B- 627204	20-08-92
		AU-B- 3933689	22-02-90
		DE-D- 68918538	03-11-94
		DE-T- 68918538	20-04-95
		ES-T- 2063135	01-01-95
		JP-A- 2107267	19-04-90